



PRODUCT TESTING SERVICES

100 Clemson Research Blvd. Anderson, SC 29625 Tel (864) 646-TILE Fax (864) 646-2821

TCNA TEST REPORT NUMBER: TCNA-280-10

PAGE: 1 OF 1

TEST REQUESTED BY: Quarry Tile Co.
Attn: Dirk Elliot
6328 E. Utah Ave
Spokane, WA 99212

TEST SUBJECT MATERIAL: Identified by client as: Quarry Tile Natural Hues


TEST DATE: 8/18/10-8/19/10

TEST PROCEDURE: ASTM C373: "Standard Test Method for Water Absorption, Bulk Density, Apparent Porosity, and Apparent Specific Gravity of Fired Whiteware Products"
-Five specimens were tested.
-The specimens were subjected to a five-hour boil and 24-hour soak to room temperature.

TEST RESULTS: The average water absorption of five (5) specimens was: **4.15%**. This value classifies the subject material as semi-vitreous (with a water absorption of more than 3.0 percent, but not more than 7.0 percent).

The individual results of water absorption were as follows:
Specimen 1: 3.50 %
Specimen 2: 4.38 %
Specimen 3: 4.32 %
Specimen 4: 4.19 %
Specimen 5: 4.34 %

[The ANSI A137.1 specification states that Pressed Floor Tile shall be classified as vitreous, semi-vitreous, or non-vitreous.]


Katelyn Simpson
Laboratory Manager

8/24/10
Date